

## Test report

**Test report relating to a structural sealant according to ETAG 002 - Guideline for European technical approval for structural sealant glazing kits (SSGK) May 2012 - concerning the product marked as: MF881-25G Silicone Structural Sealant, manufactured by: Zhengzhou Zhongyuan Silande High Technology Co., Ltd**

|                 |  |
|-----------------|--|
| Report number   | 89212213-01 REV02  |
| Date            | 16 May 2019  |
| Author(s)       | Mr. M.A.A.M. Schets, B. Sc.  |
| Client          | Zhengzhou Zhongyuan Silande High Technology Co., Ltd<br>No. 28 Dongqing West St<br>Zhengzhou Hi-tech Industrial Development Zone, Henan<br>China |
| Project number  | 89212213   |
| Project name    | 17.A196 - ETAG 002   |
| Number of pages | 30   |

*All rights reserved.*

*No part of this report may be reproduced, provided to and/or examined by third parties, and/or published by print, photoprint, microfilm, in electronic form or any other means without the explicit previous written consent of TÜV Rheinland Nederland B.V.*

*In case this report was drafted within the context of an assignment to TÜV Rheinland Nederland B.V., the rights and obligations of contracting parties are subject to the General Terms & Conditions for Advisory, Research and Certification assignments to TÜV Rheinland Nederland B.V and/or the relevant agreement concluded between the contracting parties.*

© 2010 TÜV Rheinland Nederland B.V.

## Contents

|                   |   |           |
|-------------------|---|-----------|
| <b>1</b>          | <b>Introduction</b>   | <b>3</b>  |
| 1.1               | Purpose   | 3         |
| 1.2               | Description of the samples  | 3         |
| 1.3               | Sampling procedure  | 4         |
| 1.4               | Application   | 4         |
| 1.5               | Method of testing   | 4         |
| 1.6               | Put out to contract   | 4         |
| 1.7               | Privacy statement   | 4         |
| 1.8               | Notifications, accreditations, designations                         | 4         |
| <b>2</b>          | <b>Procedure</b>  | <b>5</b>  |
| 2.1               | Test equipment and measurement uncertainty                          | 6         |
| <b>3</b>          | <b>Test results</b>   | <b>7</b>  |
| 3.1               | Initial mechanical strength   | 7         |
| 3.2               | Residual mechanical strength after artificial ageing                | 10        |
| 3.3               | Physical properties   | 13        |
| 3.4               | Identification of product   | 18        |
| <b>4</b>          | <b>Evaluation</b>   | <b>21</b> |
| <b>5</b>          | <b>References</b>   | <b>23</b> |
| <b>6</b>          | <b>Signatures</b>   | <b>25</b> |
| <b>Appendix A</b> | <b>Pictures of the tested object(s)</b>                             | <b>26</b> |
| <b>Appendix B</b> | <b>Determination of <math>K_{12.5}</math></b>                       | <b>29</b> |
| <b>Appendix C</b> | <b>Tensile strength curves sealant before and after UV exposure</b> | <b>30</b> |

# 1 Introduction

## 1.1 Purpose

The tests have been performed in order to determine the properties of a sealant according to ETAG 002 standard [1].

## 1.2 Description of the samples

### General

|                                    |  |
|------------------------------------|--|
| Name of the Manufacturer           | Zhengzhou Zhongyuan Silande High Technology Co., Ltd                                     |
| Address of the manufacturer        | No. 28 Dongqing West St<br>Zhengzhou Hi-tech Industrial Development Zone, Henan<br>China |
| Production plant of the samples    | Zhengzhou  |
| Line ID where the samples are made | Turello TMD 3000 mixer   |
| Production date                    | 2017-03-19   |
| Sampling date                      | 2017-03-25   |
| The product was marked as          | MF881-25G Silicone Structural Sealant  |
| Trade mark                         | SILANDE  |

### Specific

|                           |   |
|---------------------------|---|
| Samples<br>see annex A    | H samples; 50x50 substrate and 12x12x50 mm sealant joint (sample type 1), |
|                           | 250 mm circular 2.2 mm thick cured film (sample type 2)                   |
|                           | tubes containing MF881-25G A and B component                              |
| Sealant material          | MF881-25G Silicone Structural Sealant                                     |
| Type                      | silicone, two component   |
| Batch No.                 | Part A: 2017-03-19-11 (white)<br>Part B: 2017-03-10-12 (black)            |
| Mix ration A : B          | 12 : 1 by weight  |
| Colour                    | Black   |
| Substrate Specification   |   |
| A Type of glass (coating) | Clear float glass, no coating, 6 mm thick                                 |
| B Aluminium               | no specifications given, 3 mm thick                                       |

### **1.3 Sampling procedure**

The samples have been submitted by the assignor. The test house, acting as notified test body, has had no influence on the selection of the samples. The samples were received on 4 September 2017.

### **1.4 Application**

The request for testing was submitted by the assignor on Datum on 28 August 2017. Assignment Form number: 17.A196.

### **1.5 Method of testing**

All applicable tests have been performed according to the standard ETAG 002-1 [1].

### **1.6 Put out to contract**

No tests were performed at third parties.

### **1.7 Privacy statement**

Due to privacy reasons, the names of involved personnel that executed the tests are not disclosed in the report. However, this information is available on internal work sheets, test forms etc. in the project file.

### **1.8 Notifications, accreditations, designations**

TÜV Rheinland Nederland B.V. has been notified by the Dutch Ministry of Infrastructure and the Environment as Notified Test Body (number 1750) and Notified Certification Body (number 0336) for the European Construction Products Directive 89/106/EEC.

TÜV Rheinland Nederland B.V. has been accredited by the Dutch Accreditation Council (RvA) as ISO 17025 Test Laboratory (nr. L 484) and ISO 17065 Certification Body (nr. C078).

TÜV Rheinland Nederland B.V. has been designated as Technical Service (Laboratory) by the Approval Authorities for the Netherlands (RDW – E4) and Germany (KBA – E1) to grant approvals as mentioned in Directive 70/156/etc. and in the 1958 Agreement of the Economic Commission for Europe of the United Nations (UN-ECE) for glass as used in the automotive sector: ECE Regulation 43, safety glazing; EC Directive 92/22, Safety glass; EC Directive 2009/144, Glazing cat. T.

TÜV Rheinland Nederland B.V. has been recognised by the German Institute for building technics (DIBt) under number NL005.

## 2 Procedure

All tests were performed according to ETAG 002-1: 2012 [1]. Before testing the samples were stored for a minimum of 28 days in an air conditioned room at (23±2) °C and (50±5) % relative humidity and tested at this condition unless otherwise specified.

The following tests were conducted.

Table 2.1 Overview tests

| ETAG test §   | Characteristic                                      | Conditions  | Results   |
|---|---|---|---|
| 5.1.4.1<br>Initial<br>mechanical<br>strength                                | 5.1.4.1.1<br>Tensile strength                       | Tensile strength at<br>-20 °C / +23 °C / +80 °C<br><br>Sample type 1  | Stress at elongations of 5,<br>10, 15, 20 and 25 %;<br>Stiffness K <sub>12.5</sub> ;<br>maximum stress/strain <sup>1)</sup> ;<br>failure mode <sup>2)</sup> |
|   | 5.1.4.1.2<br>Shear strength                         | Shear strength at<br>-20 °C / +23 °C / +80 °C<br><br>Sample type 1  | Stress at relative<br>displacement of 5, 10, 15,<br>20 and 25 %;<br>maximum stress/strain;<br>failure mode  |
| 5.1.4.2<br>Residual<br>mechanical<br>strength after<br>artificial<br>ageing | 5.1.4.2.1<br>Immersion in water<br>and UV radiation | Tensile strength after 504±4 and<br>1008±4 hours exposure in<br>water/UV at (45±1) °C.<br>Glass side directed to UV light<br>source.<br>Sample type 1 | Stress at elongations of 5,<br>10, 15, 20 and 25 %;<br>maximum stress/strain;<br>failure mode   |
|   | 5.1.4.2.2<br>Salt spray exposure                    | Tensile strength after 480±4 hours<br>ISO 9226 NSS atmosphere<br>exposure.<br>Sample type 1   |   |
|   | 5.1.4.2.3<br>SO <sub>2</sub> exposure               | Tensile strength after 20 cycles ISO<br>3231 SO <sub>2</sub> atmosphere exposure.<br>Sample type 1  |   |
|   | 5.1.4.2.4<br>Façade cleaning<br>product             | Tensile strength after 21 days<br>immersion in tap water with 1%<br>dish detergent (Dreft, Procter &<br>Gamble) at (45±1) °C.<br>Sample type 1        |   |
| 5.1.4.6<br>Physical<br>properties   | 5.1.4.6.1<br>Gas inclusions                         | 1 Sample prepared by TUV<br>according to figure 14 of ETAG 002-<br>1  | Occurrence of gas<br>bubbles within 21 days   |
|   | 5.1.4.6.2<br>Elastic recovery                       | EN ISO 7389 after method A<br>conditioning 25% extension at<br>(23±2) °C.<br>Sample type 1  | Initial and final extension;<br>Elongation after 1 hour<br>unloading; recovery  |
|   | 5.1.4.6.3<br>Shrinkage                              | Volume change after conditioning in<br>accordance with ISO 10563.<br>Sample: metal rings filled with<br>sealant prepared by TUV                       | Change in volume<br>(shrinkage)   |
|   | 5.1.4.6.3<br>Resistance to                          | Tensile strength at<br>+23 °C with at two sides an incision   | Stress at elongations of 5,<br>10, 15, 20 and 25 %;   |

|                                     |  |   |   |
|-------------------------------------|--|---|---|
|                                     | tearing                                      | in the sealant.<br>Sample type 1  | maximum stress/strain;<br>failure mode  |
|                                     | 5.1.4.6.5<br>Mechanical fatigue              | Tensile strength after repetitive<br>mechanical load as per ETAG 002-<br>1 § 5.1.4.6.5<br>Sample type 1   | Stress at elongations of 5,<br>10, 15, 20 and 25 %;<br>maximum stress/strain;<br>failure mode |
|                                     | 5.1.4.6.6<br>UV resistance of<br>the sealant | Tensile strength sealant material<br>ISO 527-3 sample type 5, of<br>unexposed specimens and<br>specimens exposed to (504±4)<br>hours UV radiation (Osram Ultra<br>Vitalux lamps) as per ETAG 002-1<br>§ 5.1.4.6.6 | Tensile strength;<br>Elongation at max<br>Secant modulus at 0.5-1%<br>and between 5-25%       |
|                                     | 5.1.4.6.7<br>Elastic modulus<br>sealant      | Tensile test ISO 527-3<br>Sample type 5   |   |
|                                     | 5.1.4.6.8<br>Creep under long<br>term shear  | Simultaneous specific (static)<br>tensile and shear load for 91 days<br>Samples type 3  | Residual deformation 24<br>hours after unloading  |
| 5.2<br>Identification<br>of product | 5.2.1.1<br>Specific mass                     | Mass according to ISO 1183-1<br>method A, immersion method of<br>cured sealant<br>cut specimens from sample type 2  | Specific mass   |
|                                     | 5.2.1.2<br>Hardness                          | Shore A hardness ISO 868 of cured<br>sealant<br>cut specimens from sample type 2  | Shore A   |
|                                     | 5.2.1.3<br>Thermo gravimetric<br>analysis    | TGA plot up to 900°C from cured<br>sealant based on ISO 7111  | TGA diagram   |
|                                     | 5.2.1.4<br>Colour                            | ISO colour coordinates of<br>cured sealant  | colour coordinates  |
|                                     |  |   |   |

1) The stress and strain at rupture is interpreted as the maximum force measured and corresponding elongation.

2) The failure mode is noted as percentage of C (cohesive failure in the sealant) or A (adhesive failure at the substrate).

## 2.1 Test equipment and measurement uncertainty

All tensile tests were performed on a Zwick Z100 universal test machine with a test speed of 5 mm/min and 20 kN load cell. The displacement was measured with the crosshead movement.

Uncertainty on measured dimensions: ±0.05 mm

Tensile test

Stress  $\sigma$ : ±0.01 MPa

Strain  $\epsilon$  : ±0.5 % (absolute)

Mass: ±0.001 g

Hardness: ±1

### 3 Test results

#### 3.1 Initial mechanical strength

Tensile and shear strength at -20, +23 and +80 °C of H-sample (sample type 1) after performing all applicable conditioning steps according to the relevant ETAG 002-1 [1] paragraphs.

Table 3.1.1 Results tensile strength initial at -20 °C

|                   | K12,5             | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\epsilon$ -max | failure |
|-------------------|-------------------|--------------|---------------|---------------|---------------|---------------|---------------|-----------------|---------|
| Nr                | N/mm <sup>2</sup> | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %               | mode    |
| 1                 | 2.88              | 0.16         | 0.30          | 0.42          | 0.52          | 0.62          | 1.63          | 157             | 100% C  |
| 2                 | 2.67              | 0.14         | 0.28          | 0.39          | 0.50          | 0.60          | 1.43          | 121             | 100% C  |
| 3                 | 2.65              | 0.12         | 0.27          | 0.39          | 0.50          | 0.60          | 1.58          | 143             | 100% C  |
| 4                 | 2.73              | 0.14         | 0.28          | 0.40          | 0.50          | 0.60          | 1.27          | 95              | 100% C  |
| 5                 | 2.79              | 0.14         | 0.29          | 0.41          | 0.51          | 0.61          | 1.48          | 130             | 100% C  |
| X <sub>mean</sub> | <b>2.74</b>       | 0.14         | 0.28          | 0.40          | 0.51          | 0.61          | <b>1.48</b>   | 129             |         |
| s                 | 0.09              | 0.02         | 0.01          | 0.01          | 0.01          | 0.01          | 0.14          | 24              |         |
| R <sub>u,5</sub>  |                   |              |               |               |               |               | <b>1.14</b>   |                 |         |

Table 3.1.2 Results tensile strength initial at 23 °C

|                   | K12,5             | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\epsilon$ -max | failure |
|-------------------|-------------------|--------------|---------------|---------------|---------------|---------------|---------------|-----------------|---------|
| No.               | N/mm <sup>2</sup> | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %               | mode    |
| 1                 | 2.89              | 0.17         | 0.30          | 0.42          | 0.51          | 0.59          | 0.97          | 75              | 100% C  |
| 2                 | 3.03              | 0.19         | 0.32          | 0.43          | 0.53          | 0.61          | 0.99          | 81              | 100% C  |
| 3                 | 2.94              | 0.18         | 0.31          | 0.42          | 0.51          | 0.60          | 0.95          | 73              | 100% C  |
| 4                 | 2.90              | 0.17         | 0.30          | 0.42          | 0.52          | 0.61          | 1.08          | 105             | 100% C  |
| 5                 | 2.83              | 0.16         | 0.30          | 0.41          | 0.50          | 0.59          | 1.04          | 96              | 100% C  |
| 6                 | 2.81              | 0.16         | 0.29          | 0.40          | 0.50          | 0.58          | 1.02          | 94              | 100% C  |
| 7                 | 2.72              | 0.16         | 0.29          | 0.39          | 0.49          | 0.57          | 1.01          | 99              | 100% C  |
| 8                 | 2.73              | 0.14         | 0.28          | 0.40          | 0.50          | 0.59          | 1.11          | 113             | 100% C  |
| 9                 | 2.76              | 0.16         | 0.29          | 0.40          | 0.50          | 0.59          | 1.12          | 119             | 100% C  |
| 10                | 2.73              | 0.15         | 0.28          | 0.40          | 0.49          | 0.58          | 0.97          | 80              | 100% C  |
| X <sub>mean</sub> | <b>2.83</b>       | 0.16         | 0.30          | 0.41          | 0.51          | 0.59          | <b>1.03</b>   | 94              |         |
| s                 | 0.10              | 0.01         | 0.01          | 0.01          | 0.01          | 0.01          | 0.06          | 16              |         |
| R <sub>u,5</sub>  |                   |              |               |               |               |               | <b>0.90</b>   |                 |         |

Table 3.1.3 Results tensile strength initial at 80 °C

|                   | K12,5             | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\epsilon$ -max | failure |
|-------------------|-------------------|--------------|---------------|---------------|---------------|---------------|---------------|-----------------|---------|
| Nr                | N/mm <sup>2</sup> | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %               | mode    |
| 1                 | 2.66              | 0.13         | 0.27          | 0.39          | 0.50          | 0.59          | 0.91          | 56              | 100% C  |
| 2                 | 2.84              | 0.14         | 0.29          | 0.42          | 0.53          | 0.62          | 0.85          | 43              | 100% C  |
| 3                 | 2.84              | 0.15         | 0.29          | 0.41          | 0.52          | 0.61          | 0.92          | 57              | 100% C  |
| 4                 | 2.61              | 0.13         | 0.26          | 0.39          | 0.50          | 0.60          | 0.83          | 43              | 100% C  |
| 5                 | 2.69              | 0.13         | 0.27          | 0.40          | 0.51          | 0.60          | 0.92          | 54              | 100% C  |
| X <sub>mean</sub> | <b>2.73</b>       | 0.14         | 0.28          | 0.40          | 0.51          | 0.60          | <b>0.88</b>   | 51              |         |
| s                 | 0.11              | 0.01         | 0.01          | 0.01          | 0.01          | 0.01          | 0.04          | 7               |         |
| R <sub>u,5</sub>  |                   |              |               |               |               |               | <b>0.78</b>   |                 |         |

Table 3.1.4 Results shear strength initial at -20 °C (re-test results)

|                   | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\varepsilon$ -max | failure |
|-------------------|--------------|---------------|---------------|---------------|---------------|---------------|--------------------|---------|
| No.               | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %                  | mode    |
| 1                 | 0.04         | 0.08          | 0.12          | 0.16          | 0.19          | 1.39          | 221                | 100% C  |
| 2                 | 0.02         | 0.06          | 0.10          | 0.13          | 0.16          | 1.17          | 244                | 100% C  |
| 3                 | 0.06         | 0.10          | 0.14          | 0.17          | 0.20          | 1.27          | 225                | 100% C  |
| 4                 | 0.03         | 0.08          | 0.12          | 0.15          | 0.18          | 1.10          | 193                | 100% C  |
| 5                 | 0.03         | 0.08          | 0.11          | 0.15          | 0.18          | 1.40          | 255                | 100% C  |
| 6                 | 0.04         | 0.08          | 0.12          | 0.15          | 0.18          | 1.34          | 238                | 100% C  |
| 7                 | 0.05         | 0.09          | 0.13          | 0.16          | 0.19          | 1.27          | 235                | 100% C  |
| 8                 | 0.03         | 0.06          | 0.10          | 0.14          | 0.17          | 1.24          | 242                | 100% C  |
| 9                 | 0.05         | 0.08          | 0.12          | 0.15          | 0.19          | 1.33          | 219                | 100% C  |
| 10                | 0.05         | 0.09          | 0.13          | 0.16          | 0.19          | 1.19          | 189                | 100% C  |
| X <sub>mean</sub> | 0.04         | 0.08          | 0.12          | 0.15          | 0.18          | <b>1.27</b>   | 226                |         |
| s                 | 0.01         | 0.01          | 0.01          | 0.01          | 0.01          | 0.10          | 22                 |         |
| R <sub>u.5</sub>  |              |               |               |               |               | <b>1.06</b>   |                    |         |

Table 3.1.5 Results shear strength initial at 23 °C (re-test results)

|                   | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\varepsilon$ -max | failure |
|-------------------|--------------|---------------|---------------|---------------|---------------|---------------|--------------------|---------|
| No.               | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %                  | mode    |
| 1                 | 0.03         | 0.07          | 0.10          | 0.14          | 0.17          | 0.97          | 208                | 100% C  |
| 2                 | 0.04         | 0.08          | 0.11          | 0.14          | 0.18          | 0.78          | 155                | 100% C  |
| 3                 | 0.04         | 0.08          | 0.10          | 0.13          | 0.16          | 0.81          | 152                | 100% C  |
| 4                 | 0.04         | 0.07          | 0.11          | 0.14          | 0.18          | 0.87          | 171                | 100% C  |
| 5                 | 0.02         | 0.06          | 0.10          | 0.13          | 0.17          | 0.87          | 173                | 100% C  |
| 6                 | 0.02         | 0.06          | 0.10          | 0.14          | 0.17          | 0.74          | 196                | 100% C  |
| 7                 | 0.04         | 0.08          | 0.12          | 0.15          | 0.18          | 0.77          | 160                | 100% C  |
| 8                 | 0.05         | 0.09          | 0.13          | 0.16          | 0.19          | 0.88          | 181                | 100% C  |
| 9                 | 0.04         | 0.07          | 0.10          | 0.13          | 0.16          | 0.80          | 169                | 100% C  |
| 10                | 0.04         | 0.08          | 0.11          | 0.15          | 0.18          | 0.83          | 172                | 100% C  |
| X <sub>mean</sub> | 0.04         | 0.08          | 0.11          | 0.14          | 0.17          | <b>0.83</b>   | 173                |         |
| s                 | 0.01         | 0.01          | 0.01          | 0.01          | 0.01          | 0.07          | 18                 |         |
| R <sub>u.5</sub>  |              |               |               |               |               | <b>0.68</b>   |                    |         |



Table 3.1.6 Results shear strength at 80 °C (re-test results)

|                   | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\varepsilon$ -max | failure |
|-------------------|--------------|---------------|---------------|---------------|---------------|---------------|--------------------|---------|
| No.               | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %                  | mode    |
| 1                 | 0.04         | 0.07          | 0.11          | 0.15          | 0.18          | 0.62          | 97                 | 100% C  |
| 2                 | 0.04         | 0.09          | 0.13          | 0.16          | 0.20          | 0.65          | 99                 | 100% C  |
| 3                 | 0.02         | 0.07          | 0.11          | 0.15          | 0.18          | 0.64          | 102                | 100% C  |
| 4                 | 0.04         | 0.09          | 0.13          | 0.16          | 0.19          | 0.63          | 100                | 100% C  |
| 5                 | 0.05         | 0.09          | 0.13          | 0.17          | 0.21          | 0.69          | 91                 | 100% C  |
| 6                 | 0.04         | 0.08          | 0.12          | 0.15          | 0.19          | 0.67          | 103                | 100% C  |
| 7                 | 0.04         | 0.06          | 0.10          | 0.14          | 0.18          | 0.64          | 99                 | 100% C  |
| 8                 | 0.04         | 0.07          | 0.10          | 0.14          | 0.18          | 0.67          | 103                | 100% C  |
| 9                 | 0.03         | 0.08          | 0.11          | 0.15          | 0.18          | 0.68          | 118                | 100% C  |
| 10                | 0.03         | 0.08          | 0.12          | 0.16          | 0.19          | 0.65          | 101                | 100% C  |
| $X_{\text{mean}}$ | 0.04         | 0.08          | 0.11          | 0.15          | 0.19          | <b>0.65</b>   | 101                |         |
| s                 | 0.01         | 0.01          | 0.01          | 0.01          | 0.01          | 0.02          | 7                  |         |
| $R_{u.5}$         |              |               |               |               |               | <b>0.61</b>   |                    |         |

### 3.2 Residual mechanical strength after artificial ageing

Tensile strength of H-samples (1) after performing all applicable conditioning and or exposure steps according to the relevant ETAG 002-1 [1] paragraphs.

#### § 5.1.4.2.1 Immersion in water and UV radiation

Pre-treatment: 10 test pieces are immersed in demineralised water with a temperature of  $(45 \pm 1)^\circ\text{C}$  with the glass substrate flushed with the water level in combination with solar radiation. The U.V. source are new Osram UltraVitalux 300 W lamps. placed 25 cm from the glass surface of the samples. After  $(504 \pm 4)$  hours 5 test pieces were conditioned for 24 hours at standard laboratory conditions and subjected to a tensile test. After another  $(504 \pm 4)$  hours exposure the remaining 5 test pieces were tested after 24 hours at standard laboratory conditions.

Table 3.2.1 Results after  $(504 \pm 4)$  hours immersion in water and U.V. radiation

|                   | $K_{12.5}$ | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\varepsilon$ -max | failure |
|-------------------|------------|--------------|---------------|---------------|---------------|---------------|---------------|--------------------|---------|
| Nr                | MPa        | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %                  | mode    |
| 1                 | 2.45       | 0.16         | 0.27          | 0.36          | 0.44          | 0.51          | 0.83          | 89                 | 100% C  |
| 2                 | 2.45       | 0.14         | 0.26          | 0.35          | 0.44          | 0.51          | 0.88          | 113                | 100% C  |
| 3                 | 2.37       | 0.12         | 0.24          | 0.34          | 0.43          | 0.50          | 0.91          | 123                | 100% C  |
| 4                 | 2.45       | 0.13         | 0.25          | 0.35          | 0.44          | 0.51          | 0.88          | 108                | 100% C  |
| 5                 | 2.49       | 0.14         | 0.26          | 0.36          | 0.44          | 0.51          | 0.93          | 130                | 100% C  |
| $X_{\text{mean}}$ | 2.44       | 0.14         | 0.26          | 0.35          | 0.44          | 0.51          | <b>0.88</b>   | 113                |         |
| s                 | 0.05       | 0.01         | 0.01          | 0.01          | 0.01          | 0.00          | 0.04          | 16                 |         |
| $R_{u,5}$         |            |              |               |               |               |               | <b>0.74</b>   |                    |         |

Table 3.2.2 Results after  $(1008 \pm 8)$  hours immersion in water and U.V. radiation

|                   | $K_{12.5}$  | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\varepsilon$ -max | failure |
|-------------------|-------------|--------------|---------------|---------------|---------------|---------------|---------------|--------------------|---------|
| Nr                | MPa         | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %                  | mode    |
| 1                 | 2.32        | 0.13         | 0.24          | 0.33          | 0.41          | 0.47          | 0.81          | 115                | 100% C  |
| 2                 | 2.36        | 0.13         | 0.25          | 0.34          | 0.42          | 0.49          | 0.79          | 92                 | 100% C  |
| 3                 | 2.46        | 0.15         | 0.26          | 0.35          | 0.43          | 0.50          | 0.83          | 103                | 100% C  |
| 4                 | 2.52        | 0.16         | 0.27          | 0.36          | 0.43          | 0.50          | 0.80          | 99                 | 100% C  |
| 5                 | 2.26        | 0.12         | 0.23          | 0.33          | 0.41          | 0.47          | 0.81          | 101                | 100% C  |
| $X_{\text{mean}}$ | <b>2.38</b> | 0.14         | 0.25          | 0.34          | 0.42          | 0.49          | <b>0.81</b>   | 102                |         |
| s                 | 0.10        | 0.01         | 0.01          | 0.01          | 0.01          | 0.01          | 0.01          | 8                  |         |
| $R_{u,5}$         |             |              |               |               |               |               | <b>0.78</b>   |                    |         |

§ 5.1.4.2.2 Salt spray exposure

Table 3.2.3 Results after salt spray exposure

|                   | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\varepsilon$ -max | failure |
|-------------------|--------------|---------------|---------------|---------------|---------------|---------------|--------------------|---------|
| No.               | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %                  | mode    |
| 1                 | 0.13         | 0.26          | 0.37          | 0.46          | 0.55          | 0.90          | 83                 | 100% C  |
| 2                 | 0.14         | 0.27          | 0.38          | 0.47          | 0.55          | 0.98          | 110                | 100% C  |
| 3                 | 0.15         | 0.28          | 0.38          | 0.47          | 0.55          | 1.01          | 118                | 100% C  |
| 4                 | 0.16         | 0.29          | 0.39          | 0.48          | 0.56          | 0.94          | 99                 | 100% C  |
| 5                 | 0.17         | 0.30          | 0.40          | 0.49          | 0.57          | 1.01          | 119                | 100% C  |
| 6                 | 0.14         | 0.28          | 0.39          | 0.48          | 0.56          | 1.02          | 119                | 100% C  |
| 7                 | 0.16         | 0.29          | 0.40          | 0.50          | 0.58          | 1.01          | 114                | 100% C  |
| 8                 | 0.15         | 0.28          | 0.39          | 0.48          | 0.56          | 1.01          | 120                | 100% C  |
| 9                 | 0.15         | 0.27          | 0.38          | 0.47          | 0.55          | 0.93          | 89                 | 100% C  |
| 10                | 0.16         | 0.29          | 0.39          | 0.49          | 0.57          | 1.06          | 138                | 100% C  |
| $X_{\text{mean}}$ | 0.15         | 0.28          | 0.39          | 0.48          | 0.56          | <b>0.99</b>   | 111                |         |
| s                 |              |               |               |               |               | 0.05          |                    |         |
| $R_{u.5}$         |              |               |               |               |               | <b>0.89</b>   |                    |         |

§ 5.1.4.2.3 SO<sub>2</sub> exposure

Table 3.2.4 Results after SO<sub>2</sub> exposure

|                   | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\varepsilon$ -max | failure |
|-------------------|--------------|---------------|---------------|---------------|---------------|---------------|--------------------|---------|
| No.               | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %                  | mode    |
| 1                 | 0.15         | 0.28          | 0.39          | 0.48          | 0.57          | 0.95          | 85                 | 100% C  |
| 2                 | 0.13         | 0.26          | 0.37          | 0.47          | 0.55          | 0.98          | 102                | 100% C  |
| 3                 | 0.15         | 0.28          | 0.39          | 0.49          | 0.57          | 0.98          | 95                 | 100% C  |
| 4                 | 0.17         | 0.30          | 0.42          | 0.51          | 0.60          | 0.97          | 83                 | 100% C  |
| 5                 | 0.15         | 0.28          | 0.39          | 0.49          | 0.58          | 1.00          | 99                 | 100% C  |
| 6                 | 0.13         | 0.27          | 0.39          | 0.49          | 0.58          | 0.98          | 88                 | 100% C  |
| 7                 | 0.16         | 0.29          | 0.41          | 0.50          | 0.59          | 0.91          | 71                 | 100% C  |
| 8                 | 0.15         | 0.29          | 0.40          | 0.50          | 0.58          | 0.94          | 89                 | 100% C  |
| 9                 | 0.15         | 0.29          | 0.41          | 0.51          | 0.59          | 1.00          | 92                 | 100% C  |
| 10                | 0.15         | 0.29          | 0.40          | 0.49          | 0.58          | 0.99          | 94                 | 100% C  |
| $X_{\text{mean}}$ | 0.15         | 0.28          | 0.40          | 0.49          | 0.58          | <b>0.97</b>   | 90                 |         |
| s                 | 0.01         | 0.01          | 0.01          | 0.01          | 0.01          | 0.03          | 9                  |         |
| $R_{u.5}$         |              |               |               |               |               | <b>0.91</b>   |                    |         |

§ 5.1.4.2.4 *Façade cleaning product*

Table 3.2.5 Results after 21 days immersion in cleaning product at (45±2)°C (1 % “Dreft” solution)

|                   | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\varepsilon$ -max | failure |
|-------------------|--------------|---------------|---------------|---------------|---------------|---------------|--------------------|---------|
| Nr                | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %                  | mode    |
| 1                 | 0.14         | 0.26          | 0.35          | 0.43          | 0.49          | 0.83          | 123                | 100% C  |
| 2                 | 0.14         | 0.25          | 0.34          | 0.42          | 0.48          | 0.93          | 167                | 100% C  |
| 3                 | 0.13         | 0.25          | 0.34          | 0.42          | 0.48          | 0.85          | 138                | 100% C  |
| 4                 | 0.15         | 0.26          | 0.36          | 0.43          | 0.50          | 0.81          | 106                | 100% C  |
| 5                 | 0.15         | 0.27          | 0.36          | 0.43          | 0.49          | 0.80          | 141                | 100% C  |
| 6                 | 0.14         | 0.25          | 0.35          | 0.42          | 0.48          | 0.82          | 158                | 100% C  |
| 7                 | 0.14         | 0.25          | 0.34          | 0.42          | 0.48          | 0.79          | 117                | 100% C  |
| 8                 | 0.15         | 0.26          | 0.35          | 0.43          | 0.49          | 0.79          | 100                | 100% C  |
| 9                 | 0.15         | 0.26          | 0.35          | 0.43          | 0.49          | 0.81          | 112                | 100% C  |
| 10                | 0.14         | 0.26          | 0.35          | 0.43          | 0.49          | 0.77          | 89                 | 100% C  |
| $X_{\text{mean}}$ | 0.14         | 0.26          | 0.35          | 0.42          | 0.49          | <b>0.82</b>   | 125                |         |
| s                 | 0.01         | 0.01          | 0.01          | 0.01          | 0.01          | 0.04          | 25                 |         |
| $R_{u,5}$         |              |               |               |               |               | <b>0.74</b>   |                    |         |

### 3.3 Physical properties

#### § 5.1.4.6.1 Gas inclusions

With the sealant MF881-25G received from the client in tubes (see appendix A) a test specimen as in figure 1 was filled with the sealant. The test specimen was stored at a standard atmosphere of  $(23\pm 2) \text{ }^\circ\text{C}$  and  $(50\pm 5) \text{ } \%$  RH for 21 days. Every each 7 days the test specimen was observed visually.

*Results* : No generation of gas bubbles was observed.




Figure 1: Tests specimen for gas inclusion test

#### § 5.1.4.6.2 Elastic recovery

Three test specimens. H-samples (1). were extended by 25% of the thickness ( $\approx 3 \text{ mm}$ ) and maintained for 24 hours (see figure 2). After one hour after removing the extension. the elastic recovery of the sealant was determined (ISO 7389 [3]). After 24 hours unloading the elongation in respect to the initial elongation was determined.

Table 3.3.1 Elastic recovery at  $23 \text{ }^\circ\text{C}$

| Specimen | Extension | Elastic recovery | Elongation 24 after unloading |
|----------|-----------|------------------|-------------------------------|
| No.      | %         | %                | %                             |
| 1        | 24.5      | 98.4             | 1.3                           |
| 2        | 25.0      | 98.4             | 1.2                           |
| 3        | 24.8      | 98.6             | 1.2                           |




Figure 2: Elastic relaxation curve MF881-25G at 25 % extension.

#### § 5.1.4.6.3 Shrinkage

With the sealant MF881-25G received from the client in tubes (see appendix A) three open cylindrical rings with an internal diameter of 30 mm and 10 mm height were filled with the sealant. The mass in air ( $m_3$ ) and in water ( $m_4$ ) of the filled rings was determined 60 minutes after filling.

Hereafter the test specimen were stored at a standard atmosphere of  $(23 \pm 2)^\circ\text{C}$  and  $(50 \pm 5)\% \text{RH}$  for 28 days and then stored in an oven at  $(70 \pm 2)^\circ\text{C}$  for 7 days. After 1 day conditioning at standard atmosphere the mass in air ( $m_5$ ) and in water ( $m_6$ ) was determined.

The change in volume was calculated according to ISO 10536 [4].

Table 3.3.2 Result change in mass and volume (shrinkage)

| Specimen no. | change in mass [%] | change in volume [%] |
|--------------|--------------------|----------------------|
| 1            | 1.8                | 3.2                  |
| 2            | 1.8                | 3.2                  |
| 3            | 1.8                | 3.3                  |
| Average      | 1.8                | 3.2                  |

§ 5.1.4.6.3 Resistance to tearing

Pre-treatment: In the middle of both ends of the sealant of a sample type 1 (H- sample) a horizontal incision is made of 5 mm depth. This is done with a razor blade.

Table 3.3.3 Results tear test at 23 °C

|                   | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ | $\sigma$ -max | $\varepsilon$ -max | failure mode |
|-------------------|--------------|---------------|---------------|---------------|----------|---------------|--------------------|--------------|
| No.               | MPa          | MPa           | MPa           | MPa           | MPa      | MPa           | %                  |              |
| 1                 | 0.20         | 0.34          | 0.44          | 0.55          | 0.65     | 0.80          | 42                 | 100% C       |
| 2                 | 0.19         | 0.34          | 0.47          | 0.58          | 0.67     | 0.84          | 44                 | 100% C       |
| 3                 | 0.16         | 0.32          | 0.46          | 0.57          | 0.67     | 0.86          | 53                 | 100% C       |
| 4                 | 0.16         | 0.32          | 0.45          | 0.56          | 0.66     | 0.82          | 41                 | 100% C       |
| 5                 | 0.18         | 0.34          | 0.47          | 0.59          | 0.68     | 0.80          | 38                 | 100% C       |
| $X_{\text{mean}}$ | 0.18         | 0.33          | 0.46          | 0.57          | 0.66     | <b>0.82</b>   | 44                 |              |
| s                 | 0.02         | 0.01          | 0.01          | 0.01          | 0.01     | 0.02          | 5                  |              |
| $R_{u,5}$         |              |               |               |               |          | <b>0.78</b>   |                    |              |

§ 5.1.4.6.5 Mechanical fatigue

Pre-treatment: The 10 specimens (1) were subjected to cyclic mechanical loads before determination of the tensile strength.

The cyclic load was applied as follows:

1. 100x from 0.1  $\delta_{\text{des}}$  to 1x  $\delta_{\text{des}}$
2. 250x from 0.1  $\delta_{\text{des}}$  to 0.8x  $\delta_{\text{des}}$
3. 5000x from 0.1  $\delta_{\text{des}}$  to 0.6x  $\delta_{\text{des}}$

The  $\delta_{\text{des}}$  is determined according to ETAG 002 annex A2.1

$\delta_{\text{des}}$  = tension design stress  $\delta_{\text{des}} = R_{u,5} / \gamma_{\text{tot}}$  . with  $\gamma_{\text{tot}}$  total safety factor = 6

$\delta_{\text{des}} = 0.90 / 6 = 0.15 \text{ MPa}$

Table 3.3.4 Results tensile strength after mechanical fatigue test at 23°C

|                   | $\sigma$ -5% | $\sigma$ -10% | $\sigma$ -15% | $\sigma$ -20% | $\sigma$ -25% | $\sigma$ -max | $\varepsilon$ -max | failure mode |
|-------------------|--------------|---------------|---------------|---------------|---------------|---------------|--------------------|--------------|
| No.               | MPa          | MPa           | MPa           | MPa           | MPa           | MPa           | %                  |              |
| 1                 | 0.15         | 0.28          | 0.40          | 0.53          | 0.63          | 1.16          | 97                 | 100% C       |
| 2                 | 0.17         | 0.31          | 0.43          | 0.53          | 0.62          | 1.04          | 72                 | 100% C       |
| 3                 | 0.18         | 0.32          | 0.43          | 0.53          | 0.62          | 1.06          | 80                 | 100% C       |
| 4                 | 0.19         | 0.33          | 0.44          | 0.54          | 0.64          | 1.03          | 70                 | 100% C       |
| 5                 | 0.16         | 0.30          | 0.42          | 0.52          | 0.61          | 1.17          | 102                | 100% C       |
| 6                 | 0.18         | 0.32          | 0.44          | 0.54          | 0.63          | 1.20          | 102                | 100% C       |
| 7                 | 0.16         | 0.31          | 0.43          | 0.53          | 0.63          | 1.15          | 91                 | 100% C       |
| 8                 | 0.17         | 0.32          | 0.44          | 0.55          | 0.65          | 1.14          | 88                 | 100% C       |
| 9                 | 0.12         | 0.27          | 0.39          | 0.50          | 0.60          | 1.13          | 96                 | 100% C       |
| 10                | 0.14         | 0.29          | 0.41          | 0.51          | 0.61          | 1.04          | 73                 | 100% C       |
| $X_{\text{mean}}$ | 0.16         | 0.30          | 0.42          | 0.53          | 0.62          | <b>1.11</b>   | 87                 |              |
| s                 | 0.02         | 0.02          | 0.02          | 0.02          | 0.02          | 0.06          | 13                 |              |
| $R_{u,5}$         |              |               |               |               |               | <b>0.94</b>   |                    |              |

§ 5.1.4.6.6 *UV resistance of the sealant*

Ten test pieces as per ISO 527-3 type 5. were punched out (2.2 ±0.2) mm thick cured sealant film as received from the client (see appendix A). Five test pieces were tested as such according to ISO 527-3 at a test speed of 5 mm/min (ISO 527-3/5/5) with 0.2 N pre-stress. The other 5 test pieces were submitted to UV aging for 500 hours in a Weather-Ometer Ci 4000 according to EN ISO 4892-2 [14] exposure cycle no. 1 (Xenon lamp).

The tensile strength (maximum stress) and corresponding elongation are given in table 3.2.6. The (secant) modulus between 0.25 and 1% (near origin) and between 5 and 25 % elongation are given in table 3.2.7 before and after UV exposure.

The stress-elongation curves are represented in appendix C.

Table 3.3.5 Result tensile strength sealant before (initial) and after U.V. exposure at 23 °C

| Specimen no.            | Initial                |                | After UV exposure      |                |
|-------------------------|------------------------|----------------|------------------------|----------------|
|                         | Tensile strength [MPa] | Elongation [%] | Tensile strength [MPa] | Elongation [%] |
| 1                       | 1.54                   | 152            | 1.62                   | 178            |
| 2                       | 1.69                   | 179            | 1.66                   | 173            |
| 3                       | 1.66                   | 181            | 1.62                   | 163            |
| 4                       | 1.72                   | 193            | 1.76                   | 193            |
| 5                       | 1.82                   | 210            | 1.77                   | 190            |
| <b>X<sub>mean</sub></b> | <b>1.69</b>            | <b>183</b>     | <b>1.68</b>            | <b>179</b>     |
| S                       | 0.10                   | 21             | 0.08                   | 12             |

§ 5.1.4.6.7 *Elastic modulus sealant*

Table 3.3.6 Result elastic (secant) modulus sealant before and after UV exposure

| Specimen no.            | Elastic modulus as such [MPa] |             | Elastic modulus after UV exposure [MPa] |             |
|-------------------------|-------------------------------|-------------|---|-------------|
|                         | 0.25-1 %                      | 5-25 %      | 0.25-1 %                                | 5-25 %      |
| 1                       | 2.98                          | 2.33        | 2.62                                    | 2.09        |
| 2                       | 2.72                          | 2.25        | 2.94                                    | 2.35        |
| 3                       | 2.71                          | 2.19        | 2.62                                    | 2.24        |
| 4                       | 2.87                          | 2.37        | 2.80                                    | 2.22        |
| 5                       | 2.84                          | 2.31        | 2.86                                    | 2.31        |
| <b>X<sub>mean</sub></b> | <b>2.83</b>                   | <b>2.29</b> | <b>2.77</b>                             | <b>2.24</b> |
| s                       | 0.11                          | 0.07        | 0.14                                    | 0.10        |

§ 5.1.4.6.8 *Creep under long term shear*

Before testing 3 specimens were stored for a minimum of 28 days in an air conditioned room at (23±2) °C and (50±5) % relative humidity and tested at this condition.

The creep installation subjects simultaneously the test specimens for 91 days to:

- Tensile loading of  $M_1 = 2 * L * h * P_t$   
Where  
L: length the of the seal (mm)  
h: wide of seal (mm)  
 $P_t = 0.3 * \delta_{des}$  and  $\delta_{des} = R_{u,5} / 6$

$R_{u,5}$  is the characteristic stress value at 23°C giving 75% confidence that 95% of the test results will be higher than this value.

The  $R_{u,5}$  in tension has been determined as 0.90 MPa. see test table 3.1.2.



- Permanent shear loading of :  $M_2 = 2 * L * h * \tau_{\infty}$   
 With  $\tau_{\infty}$  stress given by the manufacturer taking into account a creep factor ( $\gamma_c$ ) of 10 as given by the manufacturer  
 No value for  $\tau_{\infty}$  was given by manufacturer.  
 For the test a value for  $\tau_{\infty}$  of  $\tau_{des} / \gamma_{tot} = (R_{u,5} / 6) / 10$  is used.

The  $R_{u,5}$  in shear has been determined as 0.75 MPa. see test table 3.1.5.

For the test the sealant length and average wide of the test specimens was used to calculate the tensile and shear loading. The load was applied with dead weights.

Table 3.3.7: Load arrangement per specimen

| Specimen | average wide (h) x length left seal [mm <sup>2</sup> ] | average wide (h) x length right seal [mm <sup>2</sup> ] | Pt MPa | $\tau_{\infty}$ MPa | Tensile load $M_1$ N (kg) | Shear load $M_2$ N (kg) |
|----------|--|---|--------|---------------------|---------------------------|-------------------------|
| 1        | 1580   | 1600  | 0.045  | 0.0125              | 143 (14.6)                | 40 (4.0)                |
| 2        | 1540   | 1560  |        |                     | 140 (14.2)                | 39 (3.9)                |
| 3        | 1560   | 1540  |        |                     | 140 (14.2)                | 39 (3.9)                |

The creep of the specimens during the test duration is shown in figure 3.

The deformation after 91 days loading and after 24 h. unloading is given in table 3.2.8.

Table 3.2.8: Deformation creep test [mm]

| Specimen | After 91 days loading | after 24 h unloading |
|----------|-----------------------|----------------------|
| 1        | 0.050                 | 0.035                |
| 2        | 0.048                 | 0.021                |
| 3        | 0.031                 | 0.023                |
| average  |                       | 0.03                 |




Figure 3: Creep sealant MF881-25G at 23°C

### 3.4 Identification of product

#### § 5.2.1.1 Specific mass

The specific mass was determined of three specimens from cured sealant film (2 mm thick) according to ISO 1183 method A immersion method (water) at (23±1) °C.

Table 3.4.1 Specific mass cured sealant at 23°C

| Test piece | Specific mass g/cm <sup>3</sup> |
|------------|---------------------------------|
| 1          | 1.573                           |
| 2          | 1.571                           |
| 3          | 1.572                           |
| Average    | 1.572                           |
| S          | 0.001                           |

#### § 5.2.1.2 Hardness

The Shore A hardness was determined according to ISO 868. From the cured 2 mm thick film samples three test pieces were made by stacking 3 layers of film on top of each other. Of each test piece 5 readings were taken after 3 seconds.

Table 3.4.2 Shore A Hardness at 23°C

| Test piece | Shore A hardness |
|------------|------------------|
| 1          | 48               |
| 2          | 48               |
| 3          | 47               |
| Average    | 48               |
| S          | 1                |

### § 5.2.1.3 Thermogravimetric analysis

The weight/mass loss of the sealant as function of the temperature was determined with a TGA Q500 TA Instruments apparatus at the following conditions based on ISO 11358-1:2014 [11]:


Temperature: 30 – 900 °C. 5 minutes isotherm at 900 °C

Heating: 10 °C/min under nitrogen atmosphere

Mass: 52.0580 mg cut from 2.2 mm thick cured film sample from manufacturer

The relative weight loss with temperature (green curve) and first derivative (blue curve) is given in figure 2. There are two main decomposition steps. In the first step up to approx. 620 °C there is a weight loss of 39.5 %. The second double decomposition step consists of a small and a larger step. Up to approx. 685 °C there is a 2.1 % weight loss and up to approx. 900 °C another 23.0 %. After 5 minutes at 900 °C a residue of 35.4 % is left.

Figure 2: TGA curve. weight loss of MF881-25G Silicone Structural Sealant up to 900 °C.



#### § 5.2.1.4 Colour

Instead of defining the colour of the sealant according to the colour scale of ISO 4660 [12] the colour coordinates were determined according to LAB colour space. Of a piece of 2.2 mm thick cured film both sides (A and B) were measured with a Minolta CM 2600 D spectrophotometer D65 illumination at an angle of 10° according to ISO 7724 [13].

Table 3.4.3 Results LAB measurements

| Test piece | L*    | a*    | b*    |
|------------|-------|-------|-------|
| side A     | 25.62 | -0.16 | -1.84 |
| side B     | 25.85 | -0.17 | -1.83 |
|            |       |       |       |

## 4 Evaluation

The requirements for safety in use (ER4) of structural glazing sealants are set out in table 8.3 of ETAG 002 part 1:2012 [1]. The test results and requirements and the sealant identification properties are summarised in table 4.1.

Table 4.1 Summary of test results and requirements

| Verification method                                  | Requirements   | Results  |
|--|--|--|
| <b>3.1 Initial mechanical strength</b>               |  |  |
| Tensile strength at -20, 23 and 80°C                 | $K_{12.5; -20/23/80^{\circ}\text{C}}$<br><br>$R_{u.5; -20/23/80^{\circ}\text{C}}$<br><br>$\Delta X_{\text{mean}} = X_{\text{mean}, -20^{\circ}\text{C}} / X_{\text{mean}, 23^{\circ}\text{C}} \geq 0.75$<br>$\Delta X_{\text{mean}} = X_{\text{mean}, 80^{\circ}\text{C}} / X_{\text{mean}, 23^{\circ}\text{C}} \geq 0.75$<br>Rupture $\geq 90\%$ cohesive | $K_{12.5; -20^{\circ}\text{C}} = 2.74 \text{ MPa}$<br>$K_{12.5; 23^{\circ}\text{C}} = 2.83 \text{ MPa}$<br>$K_{12.5; 80^{\circ}\text{C}} = 2.73 \text{ MPa}$<br>$R_{u.5; -20^{\circ}\text{C}} = 1.14 \text{ MPa}$<br>$R_{u.5; 23^{\circ}\text{C}} = 0.90 \text{ MPa}$<br>$R_{u.5; 80^{\circ}\text{C}} = 0.78 \text{ MPa}$<br>$\Delta X_{\text{mean}} = 1.48 / 1.03 = 1.44$<br>$\Delta X_{\text{mean}} = 0.88 / 1.03 = 0.85$<br>All test specimens more than 90% cohesive rupture |
| Shear strength at -20, 23 and 80°C                   | $R_{u.5; -20/23/80^{\circ}\text{C}}$<br><br>$\Delta X_{\text{mean}} = X_{\text{mean}, -20^{\circ}\text{C}} / X_{\text{mean}, 23^{\circ}\text{C}} \geq 0.75$<br>$\Delta X_{\text{mean}} = X_{\text{mean}, 80^{\circ}\text{C}} / X_{\text{mean}, 23^{\circ}\text{C}} \geq 0.75$<br>Rupture $\geq 90\%$ cohesive  | $R_{u.5; -20^{\circ}\text{C}} = 1.06 \text{ MPa}$<br>$R_{u.5; 23^{\circ}\text{C}} = 0.68 \text{ MPa}$<br>$R_{u.5; 80^{\circ}\text{C}} = 0.61 \text{ MPa}$<br>$\Delta X_{\text{mean}} = 1.27 / 0.83 = 1.53$<br>$\Delta X_{\text{mean}} = 0.65 / 0.83 = 0.78$<br>All test specimens more than 90% cohesive rupture   |
| <b>3.2 Residual strength after artificial ageing</b> |  |  |
| Immersion in hot water (1000 hours) and UV           | $\Delta X_{\text{mean}} = X_{\text{mean}} / X_{\text{mean}, \text{initial } 23^{\circ}\text{C}} \geq 0.75$<br>$0.5 \leq K_{12.5} / K_{12.5, \text{initial } 23^{\circ}\text{C}} \leq 1.10$<br>Rupture $\geq 90\%$ cohesive   | $\Delta X_{\text{mean}} = 0.81 / 1.03 = 0.79$<br>$2.38 / 2.83 = 0.84$<br>All test specimens more than 90% cohesive rupture   |
| Humidity and NaCl (salt spray test)                  | $\Delta X_{\text{mean}} = X_{\text{mean}} / X_{\text{mean}, \text{initial } 23^{\circ}\text{C}} \geq 0.75$<br>Rupture $\geq 90\%$ cohesive   | $\Delta X_{\text{mean}} = 0.99 / 1.03 = 0.96$<br>All test specimens more than 90% cohesive rupture   |
| Humidity and SO <sub>2</sub>                         | $\Delta X_{\text{mean}} = X_{\text{mean}} / X_{\text{mean}, \text{initial } 23^{\circ}\text{C}} \geq 0.75$<br>Rupture $\geq 90\%$ cohesive   | $\Delta X_{\text{mean}} = 0.97 / 1.03 = 0.94$<br>All test specimens more than 90% cohesive rupture   |
| Façade cleaning products (1% Dreft solution)         | $\Delta X_{\text{mean}} = X_{\text{mean}} / X_{\text{mean}, \text{initial } 23^{\circ}\text{C}} \geq 0.75$<br>Rupture $\geq 90\%$ cohesive   | $\Delta X_{\text{mean}} = 0.82 / 1.03 = 0.80$<br>All test specimens more than 90% cohesive rupture   |
| <b>3.3 Physical properties</b>                       |  |  |
| Gas inclusions                                       | No visible gas bubbles   | No gas bubbles observed  |
| Elastic recovery (at initial elongation of 25%)      | Elongation 24 hours after unloading shall be < 5% of the initial elongation  | Elongation after 24 hours unloading: 1.3%  |

| Verification method                                     | Requirements   | Results  |
|---|--|--|
| Shrinkage   | Shrinkage shall be less than 10%   | Shrinkage 2.6 – 3.5%   |
| Resistance to tearing                                   | Category 1<br>$\Delta X_{\text{mean}} = X_{\text{mean}} / X_{\text{mean.initial } 23^{\circ}\text{C}} \geq 0.75$<br>Category 2<br>$\Delta X_{\text{mean}} = X_{\text{mean}} / X_{\text{mean.initial } 23^{\circ}\text{C}} \geq 0.50$ | $\Delta X_{\text{mean}} = 0.82 / 1.03 = 0.80$  |
| Mechanical fatigue                                      | $\Delta X_{\text{mean}} = X_{\text{mean}} / X_{\text{mean.initial } 23^{\circ}\text{C}} \geq 0.75$<br>Rupture $\geq 90\%$ cohesive   | $\Delta X_{\text{mean}} = 1.11 / 1.03 = 1.08$<br>All test specimens more than 90% cohesive rupture   |
| U.V. resistance of the sealant                          | $\Delta X_{\text{mean}} = X_{\text{mean}} / X_{\text{mean.initial } 23^{\circ}\text{C}} \geq 0.75$<br>for elongation and stress  | Elongation:<br>$\Delta X_{\text{mean}} = 179 / 183 = 0.98$<br>Stress<br>$\Delta X_{\text{mean}} = 1.68 / 1.69 = 0.99$  |
| Elastic modulus of the sealant                          | Declared value from test   | Initial<br>$E_{\text{secant } 0.25-1\%} = 2.83 \text{ MPa}$<br>$E_{\text{secant } 5-25\%} = 2.29 \text{ MPa}$<br>After U.V. ageing<br>$E_{\text{secant } 0.25-1\%} = 2.77 \text{ MPa}$<br>$E_{\text{secant } 5-25\%} = 2.24 \text{ MPa}$ |
| Creep under long –term shear and cyclic tensile loading | Horizontal displacement after 24 hr unloading < 0.1 mm<br>Movement stabilised after 91 days  | Displacement: 0.03 mm<br><br>Yes   |
| <b>3.4 Identification of product</b>                    |  |  |
| Specific mass   | $V_{\text{mean}}$ and S  | $V_{\text{mean}} = 1.572 \text{ g/cm}^3$<br>S = 0.001 $\text{g/cm}^3$  |
| Hardness  | $V_{\text{mean}}$ and S  | $V_{\text{mean}} = 48 \text{ Shore A}$<br>S = 1 Shore A  |
| Thermogravimetric analysis                              | Thermogravimetric curve  | See at page 18   |
| Colour  | Colour parameters<br>LAB colour space  | L : 25.74 $\pm 0.13$<br>a : -0.165 $\pm 0.005$<br>b : -1.835 $\pm 0.005$   |

## 5 References

- 1 ETAG No. 002-1  
Guideline for European Technical Approval for Structural Sealant Glazing Kits (SSKK).  
Part 1:supported and unsupported systems  
European Organisation for Technical Approvals (EOTA). May 2012.
- 2 EN ISO 11431  
Building construction – Jointing products – Determination of adhesive/cohesion properties of sealants after exposure to heat, water and artificial light through glass  
European Committee for Standardization. August 2002.
- 3 EN ISO 7389  
Building construction - Jointing products - Determination of elastic recovery of sealants  
European Committee for Standardization. November 2003.
- 4 EN ISO 10563  
Building construction - Sealants - Determination of change in mass and volume  
European Committee for Standardization. July 2005.
- 5 EN ISO 9227  
Corrosion tests in artificial atmospheres - Salt spray tests  
European Committee for Standardization. May 2012.
- 6 EN ISO 3231  
Paints and varnishes - Determination of resistance to humid atmosphere containing sulfur dioxide  
European Committee for Standardization. November 1997.
- 7 EN ISO 527-1  
Plastics - Determination of tensile properties - Part 1: General principles  
European Committee for Standardization. February 2012.
- 8 EN ISO 527-3  
Plastics - Determination of tensile properties - Part 3: Test conditions for films and sheets  
European Committee for Standardization. August 1995 / C2:2002
- 9 ISO 1183-1:2004  
Plastics - Methods for determining the density of non-cellular plastics - Part 1: Immersion method, liquid pycnometer method and titration method  
International Organization for Standardization. 2004.
- 10 ISO 868:2003  
Plastics and ebonite -- Determination of indentation hardness by means of a durometer (Shore hardness)  
International Organization for Standardization. 2003.
- 11 ISO 11358-1:2014  
Plastics -- Thermogravimetry (TG) of polymers -- Part 1: General principles  
International Organization for Standardization. 2014

- 12 ISO 4660:2011  
Rubber. raw natural -- Colour index test  
International Organization for Standardization. 2011
- 13 ISO 7724-2:1984  
Paints and varnishes -- Colorimetry -- Part 2: Colour measurement  
International Organization for Standardization. 1984
- 14 EN ISO 4892-2:2006  
Plastics - Methods of exposure to laboratory light sources – Part 2: Xenon-arc lamps (ISO 4892-2:2006)



## 6 Signatures

|   |  |
|---|--|
| <b>Author</b><br>Mr. M.A.A.M. Schets. B.Sc. | Signature<br>  |
| Specialist                                  |  |
| <b>Peer review</b><br>Mr. R. Brandhorst     | Signature<br>  |
| Specialist                                  |  |
| <b>Approved by</b><br>Mr. H. van Ginkel     | Signature<br> |
| LSM   |  |

## Appendix A Pictures of the tested object(s)



Sample type 1 (H-sample) 6 mm float glass. 3 mm anodised aluminium. seal joint 12x12x50 mm




Sample type 1 (H-sample) typical failure pattern

Sample type 2 and ISO 527 type 5 specimens punched from 2 mm sealant film




Sample type 3. creep behaviour




$h = 7.8 - 8.0 \text{ mm}$   
 $e = 6 \text{ mm}$   
 $L = 200 \text{ mm}$

Tubes with sealant Silande MF881-25G




## Appendix B Determination of $K_{12.5}$




The secant stiffness at 12.5 % strain ( $K_{12.5}$ ) was calculated from a new zero point to compensate for irregularities and pre load at the start. This zero point was determined for each curve based on the slope of the curve at the start.

## Appendix C Tensile strength curves sealant before and after UV exposure



Tensile strength sealant as received



Tensile strength sealant after UV exposure.