

Evidence of Performance

Of the physical attributes of the edge seals
of insulating glass units according to DIN EN 1279-4



Test Report
no. 17-002666-PR10
(PB-H01-09-en-02)


Client	ZHENGZHOU ZHONGYUAN SILAND HIGH TECHNOLOGY CO., LTD No. 28 Dongqing West St, Zhengzhou Hi-tech Development Zone 450001 Zhengzhou China
Product	Structural sealant for use in the edge seals of insulating glass units
System designation	Silicone sealant, MF881-25HM, original client (desposited at ift)
Order	Test according to DIN EN 1279-4

Basis
DIN EN 1279-4 : 2002-10;
Glass in building – Insulating glass units;
Part 4: Methods of test for the physical attributes of edge seals.
Chapter: 5.1 Adhesion
Chapter: 5.2 Moisture vapour transmission rate
Chapter: 5.3 Gas permeation rate

Replaced Test Report
No. 17-002666-PR10 (PB-H01-09-en-01) dated 19.10.2017

The sealant based on Silicone, MF881-25HM, made by original client (desposited at ift), displays the following properties according to DIN EN 1279-4:

Instructions for use
This test report serves to demonstrate the physical attributes of edge seals of insulating glass units.
It serves as a basis for substitution of sealants used in insulating glass units according to EN 1279-1.



5.1 Adhesion


The requirements of DIN EN 1279-4, chapter 5.1, stress-strain behaviour, are fulfilled



5.2 Moisture vapour transmission rate

$MVTR = (16.6 \pm 0.6) \frac{\text{Gramm H}_2\text{O}}{\text{m}^2 \cdot 24\text{h} \cdot 2\text{mm}}$

Validity
The data and results given relate solely to the tested and described specimen.



5.3 Gas permeation rate

$(823 \pm 25) \times 10^{-3} \text{ g}/(\text{m}^2 \text{ h})$

Notes on publication
The ift-Guidance Sheet 'Conditions and Guidance for the Use of ift Test Documents' applies.
The cover sheet can be used as an abstract.

ift Rosenheim
29.11.2017

Michael Freinberger, Dipl.-Ing. (FH)
Head of Testing Department
Material Testing

Jennifer Seyfang, Dipl.-Ing. (FH)
Operating Testing Officer
Material Testing

Contents
The report contains a total of 12 page/s
1 Object
2 Procedure
3 Detailed results
4 Summary

The physical attributes of the edge seals of insulating glass units according to DIN EN 1279-4

Test Report 17-002666-PR10 (PB-H01-09-en-02) dated 29.11.2017

Client ZHENGZHOU ZHONGYUAN SILAND HIGH TECHNOLOGY CO., LTD,
450001 Zhengzhou (China)

1 Object

1.1 Test specimen for the adhesion test

Subject	H-specimen consisting of float glass and sealant (Fig. 1)
Manufacturer	original client (desposited at ift)
Date of manufacture	11th May 2014
Substrates A and B	Floatglas according to DIN EN 572-2
Dimensions (l x w x h) in mm	75 x 12 x 6
Sealant	
Product designation	Silicone sealant, MF881-25HM, original client (desposited at ift)
Type	Two component silicone structural sealant
	Batch No. A: no further information
	Batch No. B: no further information
Manufacturer	original client (desposited at ift)
Colour	black
Dimensions (l x w x h) in mm	50 x 12 x 12

Maße in Millimeter




Fig. 1 Geometry of the test specimen

The physical attributes of the edge seals of insulating glass units according to DIN EN 1279-4

Test Report 17-002666-PR10 (PB-H01-09-en-02) dated 29.11.2017

Client ZHENGZHOU ZHONGYUAN SILAND HIGH TECHNOLOGY CO., LTD,
450001 Zhengzhou (China)**1.2 Test specimen for testing the moisture vapour transmission rate and the gas permeation rate**

Subject	Sealant films
Manufacturer	original client (desposited at ift)
Date of manufacture	11th May 2014
Sealant	
Product designation	Silicone sealant, MF881-25HM, original client (desposited at ift)
Type	Two component silicone structural sealant
	Batch No. A: no further information
	Batch No. B: no further information
Manufacturer	original client (desposited at ift)
Colour	black
Dimensions diameter in mm	Approx. 200
Thickness in mm	Approx. 2 ± 0.1 mm

The description is based on inspection of the test specimen at **ift**.

Item designations/numbers as well as material specifications were given by the original client (desposited at ift).

The physical attributes of the edge seals of insulating glass units according to DIN EN 1279-4

Test Report 17-002666-PR10 (PB-H01-09-en-02) dated 29.11.2017

Client ZHENGZHOU ZHONGYUAN SILAND HIGH TECHNOLOGY CO., LTD,
450001 Zhengzhou (China)**2 Procedure****2.1 Sampling**

The samples were selected and produced by the original client (desposited at ift).

2.1.1 Test specimen for the adhesion test

Quantity	40 pieces as shown in Fig. 1
Delivered	16th June 2014 by the original client (desposited at ift)
Registration No.	37249

2.1.2 Test specimens for testing the moisture vapour transmission rate (MVTR)

Quantity	5 films
Delivered	16th June 2014 by the original client (desposited at ift)
Registration No.	37249

2.1.3 Test specimen for testing the gas permeation rate

Quantity	5 films
Delivered	16th June 2014 by the original client (desposited at ift)
Registration No.	37249

2.2 Process

Basis

DIN EN 1279-4 : 2002-10	Glass in building – Insulating glass units. Methods of test for the physical attributes of edge seals. Chapter 5.1 Adhesion Chapter 5.2 Moisture vapour transmission rate Chapter 5.3 Gas permeation test on film
-------------------------	---

Boundary conditions According to the requirements of the standard

Deviations There have been no deviations from the test method and test conditions

The physical attributes of the edge seals of insulating glass units according to DIN EN 1279-4

Test Report 17-002666-PR10 (PB-H01-09-en-02) dated 29.11.2017

Client ZHENGZHOU ZHONGYUAN SILAND HIGH TECHNOLOGY CO., LTD,
450001 Zhengzhou (China)**2.3 Test equipment****2.3.1 Adhesion**

Normal climate chamber	Appliance number: 22040
Airflow oven	Appliance number: 22159
UV source (Osram Vitalux)	Appliance number: 22604
Heatable water bath	Appliance number: 22509
Material testing machine acc. to DIN EN ISO 7500-1	Appliance number: 22933

2.3.2 Moisture vapour transmission rate

Normal climate chamber	Appliance number: 22040
Precision balance	Appliance number: 22431
Test chamber with hygrostat	Appliance number: 22589
moisture sensor	Appliance number: 22562

2.3.3 Gas permeation rate on film

Normal climate chamber	Appliance number: 22040
Gasleakage measurement device with gas chromatograph	Appliance number: 22503

2.4 Testing

Date/Period	17th June 2014 to 14th July 2014
Testing personnel	Miriam Kaube, B.Eng. (FH) Thomas Eder Stefan Schwarz



3 Detailed results

3.1 Adhesion test according to DIN EN 1279-4, Chapter 5.1

Tables 1 to 4 show the results of adhesive tensile strength tests following appropriate conditioning of the test specimens. Figs. 2 to 5 show the stress-strain diagrams for new condition and for the effects of the various types of exposure, with the triangle AOB shown in each case.

Table 1 Tensile strength test in new condition following curing

Test specimen number	Force F_{max} in N	Displacement s at F_{max} in mm	Stress in MPa	Strain in %	Intersection with section AB	
					Stress in MPa	Strain in %
New 1	698	5.04	1.16	42	0.41	9.6
New 2	747	4.83	1.25	40	0.41	9.2
New 3	821	5.68	1.37	47	0.42	8.4
New 5	738	4.56	1.23	38	0.41	9.2
New 7	751	4.68	1.25	39	0.42	8.5
Average					0.41	9.0




Fig. 2 Stress-strain diagram of test specimen in new condition following curing

Table 2 Tensile strength test following heat exposure 60 °C / 168 h

Test specimen number	Force F_{max} in N	Displacement s at F_{max} in mm	Stress in MPa	Strain in %	Intersection with section AB		
					Stress in MPa	Strain in %	
Heat 1	742	3.80	1.24	32	0.42	8.1	
Heat 2	805	4.30	1.34	36	0.42	8.1	
Heat 3	714	3.80	1.19	32	0.42	8.7	
Heat 5	751	3.92	1.25	33	0.42	8.1	
Heat 6	732	3.86	1.22	32	0.42	8.7	
Average						0.42	8.3




Fig. 3 Stress-strain diagram of test specimen following heat exposure

Table 3 Tensile strength test following water immersion

Test specimen number	Force F_{max} in N	Displacement s at F_{max} in mm	Stress in MPa	Strain in %	Intersection with section AB		
					Stress in MPa	Strain in %	
Water 1	673	5.48	1.12	46	0.41	9.2	
Water 3	714	6.05	1.19	50	0.42	8.8	
Water 4	623	4.47	1.04	37	0.41	9.8	
Water 5	724	5.88	1.21	49	0.41	9.3	
Water 7	702	6.22	1.17	52	0.41	9.3	
Average						0.41	9.3




Fig. 4 Stress-strain diagram of test specimen following water immersion



Table 4 Tensile strength test following UV exposure

Test specimen number	Force F_{max} in N	Displacement s at F_{max} in mm	Stress in MPa	Strain in %	Intersection with section AB	
					Stress in MPa	Strain in %
UV 1	782	4.30	1.30	36	0.42	8.8
UV 2	745	3.89	1.24	32	0.42	8.5
UV 3	752	9.96	1.25	33	0.42	8.0
UV 5	762	3.95	1.27	33	0.42	8.0
UV 6	758	4.02	1.26	33	0.42	8.0
Average					0.42	8.3




Fig. 5 Stress-strain diagram of test specimen following UV exposure



3.2 Moisture vapour transmission rate test according to DIN EN 1279-4. Chapter 5.2

Table 5 shows the moisture vapour transmission rate results for three test specimens. The moisture vapour transmission rate can be found from the gradient of the lines in the graph (Fig. 6).

The moisture vapour transmission rate is calculated according to the following formula:

$$MVTR = \frac{G}{tA} = \frac{G/t}{A}$$

G = Mass change, grams of H₂O

t = Time in days (24 h)

G/t = Gradient of the lines, grams of H₂O x (24 h)⁻¹

A = Area tested in m²

Table 5 Testing moisture vapour transmission rate on films

	Sample 1	Sample 3	Sample 5
Slope of the regression line	0,1332	0,1379	0,1360
Membrane thickness in mm	2.0	1.9	2.0
Tested area in m ²	0.0078	0.0079	0.0074
MVTR g_{H2O}/(m²*1d*2mm)	17.350	16.378	16.127
MVTR (average value)	(16.6 ± 0.6) g_{H2O}/(m²*1d*2mm)		

Error of measurement in the test procedure according to EN 1279-4, Annex C, is specified as 25 % standard deviation from the average value




Fig. 6 Graph of the moisture vapour transmission rate of 3 test specimen

The physical attributes of the edge seals of insulating glass units according to DIN EN 1279-4

Test Report 17-002666-PR10 (PB-H01-09-en-02) dated 29.11.2017

Client ZHENGZHOU ZHONGYUAN SILAND HIGH TECHNOLOGY CO., LTD,
450001 Zhengzhou (China)

3.3 Gas permeation rate, test according to DIN EN 1279-4, Chapter 5.3

The gas permeation rate test was carried out on three test specimens. The testing area of the films was approx. 0.006 m². Once a constant state had been reached, the value of the average gas permeation rate for each of the films was determined on the basis of four measurements. The results are presented in table 6.

Table 6 Gas permeation rate test on films

	Gas permeation rate in g/m ² h		
	Test specimen 1	Test specimen 2	Test specimen 3
Membrane thickness in mm	2.0	2.1	1.9
Average value for the measured film	841 x 10 ⁻³	737 x 10 ⁻³	860 x 10 ⁻³
Average value for film (relating to 2 mm membrane thickness)	846 x 10 ⁻³	797 x 10 ⁻³	826 x 10 ⁻³
Average value of gas permeation rate calculated from the 3 individual values	(823 ± 25) x 10⁻³ g/(m² h)		

Error of measurement in the test procedure according to EN 1279-3 is specified as 20 % standard deviation for all individual values.

The physical attributes of the edge seals of insulating glass units according to DIN EN 1279-4

Test Report 17-002666-PR10 (PB-H01-09-en-02) dated 29.11.2017

Client ZHENGZHOU ZHONGYUAN SILAND HIGH TECHNOLOGY CO., LTD,
450001 Zhengzhou (China)

4 Evaluation and summary according to the specifications of DIN EN 1279-4

Client: ZHENGZHOU ZHONGYUAN SILAND HIGH TECHNOLOGY CO., LTD
No. 28 Dongqing West St,
Zhengzhou Hi-tech Development Zone
450001 Zhengzhou
China

Sealant specification: Silicone sealant, MF881-25HM, original client (desposited at ift)
Glass specification: Floatglas according to DIN EN 572-2

4.1 Adhesion test

Table 7 Summary of results

Tested strength of edge seal	at the intersection with line A-B (EN 1279-4. Fig. 1)		Failure pattern						
	Average stress σ_{av} in MPa	Average strain ε_{av} in %	k = cohesive oA = no evaluation						
Adhesion			1	2	3	4	5	6	7
After curing	0.41	9.0	k	k	k	oA	k	oA	k
After heat exposure 60 °C	0.42	8.3	k	k	k	oA	k	k	oA
After water immersion	0.41	9.3	k	oA	k	k	k	oA	k
After UV exposure	0.42	8.3	k	k	k	oA	k	k	oA

4.2 Moisture vapour transmission rate test

Film thickness	Based on a thickness of 2 mm
ΔP_{H_2O}	Initial load on desiccant 2.5 %; Climatic chamber average 98.2 %rh; $\Delta P_{H_2O} = 95.7$ %
Temperature	(23±1) °C
Moisture vapour transmission rate	(16.6 ± 0.6) $\frac{\text{Gramm H}_2\text{O}}{\text{m}^2 \cdot 24\text{h} \cdot 2 \text{ mm}}$

4.3 Gas permeation rate test

Film thickness	Based on a thickness of 2 mm
Surface	Average approx. 0.006 m ²
Gas permeation rate	(823 ± 25) x 10⁻³ g/(m² h)

Result of the testing of the strength of the edge seal:

The sealant Silicone sealant, MF881-25HM, original client (desposited at ift), fulfils the criteria: **YES**

ift Rosenheim